



Dudick inc.

Corporate Offices
1818 Miller Parkway
Streetsboro, OH 44241
330-562-1970
330-562-7638 FAX
www.dudick.com

PROTECTO-COAT 300

**100% SOLIDS, HIGH BUILD EPOXY
COATING; BUILDS TO 15-20 MILS DFT
PER COAT OR THINNED 8-10 MILS DFT**

FEATURES

USDA & FDA Compliant
Meets all VOC Requirements
No Volatile Organic Compounds
Low Odor
Environmentally Safe
Fast Setting
Anti-Microbial

RECOMMENDED APPLICATIONS

**Storage Tanks, including water, high or low fat dairy products and beverages containing alcohol.

Chemical Plant Process Piping
Waste Treatment Clarifiers
Structural Steel Components
Food & Beverage Processing Facilities
Clean Rooms

CHEMICAL RESISTANCE

Dilute Inorganic Acids Salt & Brine
Aliphatic Hydrocarbons Mineral Oils
Sodium Hydroxide
Ammonium Hydroxide

TEMPERATURE LIMITS (METAL APPLICATIONS)

Immersion up to 120° F
Dry - 250°F - Continuous
300°F - Intermittent

COLORS: Standard Color Chart available upon request.

PHYSICAL PROPERTIES

Taber Abrasion 120 mg.
ASTM D-4060

Flame Spread <5 mm. self extinguish
ASTM D-635

VOC 10 gm/l
ASTM D-3960

WVT 0.0018 perm. in.
ASTM E-96

Fungus Resistance No Growth
U.S. Mil Std. 810E

****Protecto-Coat 300** meets the specifications for extraction studies in accordance with CFR Title 21,175.300, Polymeric and Resinous Coatings. Analytical reports are available on request.

SPECIFICATIONS

Protecto-Coat 300 shall be an amine cured epoxy coating applied in one or two 15-20 mil coats as manufactured by Dudick, Inc. Material shall be applied by brush, roller, or spray in accordance with the manufacturer's recommended practices. If **Protecto-Coat 300** is thinned with xylene @ 2 to 3 ounces per gallon it can be applied in 8-10 mil layers.

THE PROTECTO-COAT 300 SYSTEM

Protecto-Coat 300 uses a moisture-tolerant primer and one or two coats of low odor epoxy resin to achieve high build and provide protection for metal and concrete substrates.

Primer 67 is designed to prevent abrasive blasted steel from developing rust bloom prior to the application of the **Protecto-Coat 300**. For maximum performance, all metal

surfaces should be primed, but primer may not be needed for mild, non-immersion service. Concrete must be primed to aid in the “wetting out” required for good bonding.

Primer 67C is designed for applications on concrete where spark testing is required or specified.

Basecoat/Topcoat: The unique hybrid binder and flake fillers in **Protecto-Coat 300** provide the low permeability, high film integrity, and excellent chemical resistance required for prolonged substrate protection.

For atmospheric exposure, a single 8-10 mil DFT application of **Protecto-Coat 300** may be sufficient. Total DFT (with primer) should be 9-11 mils, minimum.

For heavy spillage or total immersion areas, two 8-10 mil finished coats can be applied over primer to achieve a DFT of 16-20 mils.

If time constraints require short coating windows **Protecto-Coat 300** can be applied un-thinned in one (1) coat 15-20 mils DFT.

However, because conditions can vary widely between these two extremes (as when concentrated fumes or only occasional spillage is encountered), a DFT between 8 and 16 mils may be adequate and more economical. Consult a Dudick Representative with specific conditions and applications.

ESTIMATING QUANTITIES AND ORDER BILL OF MATERIAL – 100% Solids

APPROXIMATE SQUARE FEET PER GALLON**	
PRIMER -See specified primer data sheet	
Protecto-Coat 300	
1st Coat	80-100 ft. ² @ 15-20 mils
2nd Coat	80-100 ft ² @ 15-20 mils

**Quantities shown are for estimating purposes only. Actual field usage may vary.

APPLICATION INSTRUCTIONS

SURFACE PREPARATION

Metal: Metal surfaces must be abrasive blasted to an appropriate finish.

Immersion and heavy spillage service: White Metal, SSPC SP 5 or NACE #1, minimum 3.0 mil profile. Heavy non-immersion service (i.e. fumes and spillage): Near white, SSPC SP 10 or NACE #2, minimum 2.0 mil profile. Atmospheric service: Commercial SSPC SP 6 or NACE #3, minimum 2.0 mil profile.

Concrete: Concrete must be mechanically prepared to remove surface laitance. Oils, grease or other contaminant must be removed prior to surface preparation. Concrete must be free of curing compounds and form release agents. Surface texture should be similar to 40-60 grit sandpaper or the visual standard, CSP-5 from the International Concrete Repair Institute **with exposed pea gravel**. The prepared surface should have a minimum tensile strength of 250 PSI per ASTM D-4541.

All concrete substrates must be checked for moisture prior to product application using the Plastic Sheet Test, ASTM D-4263.

Additional surface preparation will be required if a 60-80 grit texture is not achieved and the surface laitance not completely removed with the first mechanical preparation procedure.

Mechanical preparation removes laitance, exposing honeycombs or voids beneath the surface which must be filled with **Scratch Coat 300**. (Refer to separate product bulletin)

APPLICATION SPECIFICATIONS

Substrate temperature for both concrete and metal must be between 50°F and 110°F.

Relative humidity must not exceed 90%.

Substrate temperature must be 5°F above the Dew Point.

PRIMER 67/67C MIX RATIOS (BY VOLUME)

Primer 67	Component A	1 gallon
Primer 67	Component B	1 gallon
Primer 67C	Component A	1 gallon
Primer 67C	Component B	29 fl. oz.

Heated plural component spray equipment or thinning will aid in application of Protecto-Coat 300 – Consult Dudick, Inc. for additional information.

Important - With all epoxies after priming and before each additional coat, examine the surface for amine blush (oily film). If present, remove by washing with warm water and detergent.

The pot life of **Protecto-Coat 300** system components will depend upon the temperature. To prevent material waste and avoid damage to equipment, do not mix more material than can be used according to the Work Life & Cure Time charts.

Do not attempt to store mixed material. Residual material should be properly disposed of at the end of each work period.

Application of **Protecto-Coat 300** in direct sunlight may lead to blistering, pinholes, or wrinkling due to outgassing of air in the concrete and high substrate temperatures. Double priming, shading or evening application may be required. Consult a Dudick representative. **Protecto-Coat 300** system is intended for interior use only.

Do not attempt to store mixed material. Residual material should be properly disposed of at the end of each work period.

SPRAY SPECIFICATION FOR THINNED PROTECTO-COAT 300 EQUIPMENT

Same equipment as with 100% Solids except the tip size should range between 0.015 – 0.019 inch. For this application 2 to 3 ounces of xylene per gallon should be added.

Brush or roller application may require additional coats to meet the specified dry film thickness.

If these recoat times are exceeded, consult a Dudick representative; sanding or abrasive blasting may be required before the next coat.

Recoat times are dramatically reduced when the coating is exposed to direct sunlight.

Application of **Protecto-Coat 300** in direct sunlight may lead to blistering, pinholes, or wrinkling due to outgassing of air in the concrete and high substrate temperatures. Double priming, shading, or evening

application may be required. Consult a Dudick representative.

TESTING

Where immersion service is required, spark test the coating with a 2000 volt AC spark tester. Mark and repair all pinholes using **Protecto-Coat 300**. Retest only the repairs.

CLEANING

Use **S-10 Cleaning Solvent** to clean tools and equipment.

SHIPPING

Refer to Material Safety Data Sheets.

STORAGE

Warning: All Dudick products classified by DOT with either white, yellow or red labels must not be mixed or stored together as an explosive reaction can occur.

All products should be stored in a cool, dry area, away from open flames, sparks, or other hazards.

When properly stored in their original, unopened containers at 50°F-75°F, the **Primer 67** components will have a six-month shelf life. **Primer 67C** components will have a thirty-day shelf life. **Protecto-Coat 300** will have a six-month shelf life. Storage in direct sunlight or excessive heat will reduce working time and shelf life.

SAFETY

M.S.D.S.: Material Safety Data Sheets must always be read before using products. **Protecto-Coat 300** systems are intended for application by experienced, professional personnel. Dudick, Inc. can supply supervision to help determine that the surface has been properly prepared, the ingredients correctly mixed, and the materials properly and safely applied.

If **Protecto-Coat 300** materials are to be applied by your own personnel or by a third party contractor, please be sure that they are aware of the following safety precautions:

- Exposure to resins and hardeners through direct skin contact and/or inhalation may cause severe dermatitis reactions in some people.



Corporate Offices
1818 Miller Parkway
Streetsboro, OH 44241
330-562-1970
330-562-7638 FAX
www.dudick.com

PROTECTO-COAT 300

**100% SOLIDS, HIGH BUILD EPOXY
COATING; BUILDS TO 15-20 MILS DFT
PER COAT OR THINNED 8-10 MILS DFT**

- Cleanliness of the skin and clothing is critical and must be of paramount concern.
- Fumes are flammable and heavier than air. Proper ventilation should be maintained to minimize breathing of concentrated fumes.
- Suitable respirators should be used during application.
- Safety glasses, gloves, and suitable protective clothing must be worn at all times during application.
- If contact with hardeners occurs, remove any clothing involved and flush the skin with flowing water. Discard the clothing. Do not attempt to wash and reuse it. **Protecto-Coat 300** liquid can be removed with S-10 Cleaning Solvent, MEK, or lacquer thinner.
- Keep open flames and sparks away from the area where materials are being mixed and applied.
- If a rash occurs, remove the individual from the work area and seek a physician's care for dermatitis.
- In case of eye contact, flush with water for at least 15 minutes and consult a physician.
- If swallowed, do not induce vomiting; call a physician immediately.

NOTE: Dudick, Inc. ("Dudick") warrants all goods of its manufacture to be as represented in its catalogs and that the manufacture of its products by its employees or sub-contractors shall be performed in a workmanlike manner. Dudick's sole obligation under this warranty shall be to replace any material which its examination shall disclose to be defective. Dudick makes no warranty concerning

the suitability of its product for application to any surface, it being understood that the goods have been selected and the application ordered by the Purchaser. DUDICK, INC. MAKES NO WARRANTY, EXPRESS OR IMPLIED, THAT THE GOODS SHALL BE MERCHANTABLE OR THAT THE GOODS ARE FIT FOR ANY PARTICULAR PURPOSE. THE WARRANTY OF REPAIR OR REPLACEMENT SET FORTH HEREIN IS EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES ARISING BY LAW OR OTHERWISE; AND DUDICK INC. SHALL NOT BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES, INCLUDING BUT NOT LIMITED TO LOST PROFITS, DOWN TIME, DAMAGES TO PROPERTY OF THE PURCHASER OR OTHER PERSONS, OR DAMAGES FOR WHICH THE PURCHASER MAY BE LIABLE TO OTHER PERSONS, WHETHER OR NOT OCCASIONED BY DUDICK'S NEGLIGENCE. This warranty shall not be extended, altered or varied except by written instrument signed by Dudick and Purchaser.

3/17/10