



Dudick inc.

Corporate Offices
1818 Miller Parkway
Streetsboro, OH 44241
330-562-1970
330-562-7638 FAX
www.dudick.com

CAULK 149

**100% SOLIDS, TWO-COMPONENT
POLYSULFIDE EXPANSION/
CONTROL JOINT SEALANT**

FEATURES

Meets all VOC Requirements
Low Odor
Premeasured Units
USDA Compliant

RECOMMENDED APPLICATIONS

Secondary Containment
Process Areas
Plating
Pharmaceutical
Electronics
Power Stations

CHEMICAL RESISTANCE

Organic Acids
Inorganic Acids
Salts
Oils
Alkali Solutions

PHYSICAL PROPERTIES

Color	Gray
Specific Gravity	1.6
Tensile Strength ASTM D-412	250 PSI
Elongation ASTM D-412	500 – 550%
Hardness Shore ASTM D-2240	30 - 35
VOC ASTM D-3960	0
Density 100 lbs. / cu. ft.	13.3 lbs. / gallon

SPECIFICATIONS

Caulk 149 shall be a two-component, 100% solids, and polysulfide polymer-based joint sealant, applied in accordance with the manufacturer's recommended practices.

ESTIMATING QUANTITIES AND ORDER BILL OF MATERIAL

	CONCRETE
Primer 67	150 ft. ² / gallon
Caulk 149	346 cu. in./ 1.5 gallon
S-10 Solvent	500 sq. ft./gallon
Width x Depth Joint Size	Unit Coverage Rate Lin. Ft./ 1.5 Gal.
1 1/2" x 3/4"	25.5
1" x 1/2"	57
3/4" x 3/8"	102

Note: For best results, depth is equal to 1/2 joint width. For vertical and overhead joints, increase size by 50%.

Quantities shown are for estimating purposes only. Actual field usage may vary. **Caulk 149** is available in 1.5 gallon units only.

APPLICATION INSTRUCTIONS

SURFACE PREPARATION

Concrete: Refer to specific product bulletin where **Caulk 149** is being used for concrete surface preparation requirements.

APPLICATION SPECIFICATIONS

Substrate temperature for concrete must be between 50°F and 110°F.

Relative humidity must not exceed 90%.

Substrate temperature must be 5°F above the Dew Point.

PRIMER 67 MIX RATIO (BY VOLUME)

Component A 1 gallon
Component B 1 gallon

PRIMER 67 POT LIFE

TEMPERATURE	POT LIFE
50°F	90 min.
75°F	60 min.
90°F	30 min.

PRIMING

The following Primers are compatible with **Caulk 149**: Primer 67, Primer 67LV, Primer 67DPLV, Primer 67DTO & Primer 60.

POT LIFE AND CURE CYCLE

Temperature	Pot Life	Cure Time
50°F	6 hrs.	72 hrs.
75°F	2 hrs.	24 hrs.
90°F	1.5 hrs.	20 hrs.

Joint surfaces must be clean and dry before applying the sealant.

CAULK 149

Component A and Component B are supplied in pre-measured quantities which yield 1.5 gallons when mixed. Partial batches are not recommended.

Combine the **A and B Components** and mix mechanically using a slow speed drill (150-200 RPM) for 1-2 minutes. Scrape the sides and bottom of the pail and mix for an additional 1-2 minutes until a uniform color is achieved.

The best practice in most cases is to mask the joint before application to ensure neatness. **Caulk 149** can be applied using trowels, putty knives, spatulas or hand loaded caulking guns. Tooling the material firmly and uniformly will compact the sealant to fill voids and optimize wetting of the joint interfaces.

Dudick construction details should be referenced for illustrations regarding the correct use of backer rods and bond breaking tape.

Observe the cure schedule and allow sufficient time before placing the area into traffic conditions or chemical exposure.

CLEANING

Use **S-10 Cleaning Solvent** to clean tools and equipment.

SHIPPING

Refer to Material Safety Data Sheets.

STORAGE

Warning: All Dudick products classified by DOT with either white, yellow or red labels, must not be mixed or stored together as an explosive reaction might occur. All products should be stored in a cool, dry area away from open flames, sparks or other hazards.

When properly stored in their original, unopened containers at 50°F-75°F, **Primer 67 and Caulk 149** will have a six-month shelf life. Exposure to excessive heat may cause premature gelling, reduce working time and shelf life.

SAFETY

M.S.D.S.: Material Safety Data Sheets must always be read before using products. **Caulk 149** is intended for application by experienced, professional personnel. Dudick, Inc. can supply supervision to help determine that the surface has been properly prepared, the ingredients correctly mixed, and the materials properly and safely applied.

If materials are to be applied by your own personnel or by a third party contractor, please be sure that they are aware of the following safety precautions:

- Exposure to resins and hardeners through direct skin contact and/or inhalation may cause severe dermatitis reactions in some people. Cleanliness of the skin and clothing is critical and must be of paramount concern.
- Fumes are flammable and heavier than air. Proper ventilation should be maintained to minimize breathing of concentrated fumes.
- Suitable respirators should be used during application.
- Safety glasses, gloves, and suitable protective clothing must be worn at all times during application.
- If contact with hardeners occurs, remove any clothing involved and flush the skin with flowing water. Discard the clothing. Do not attempt to wash and reuse it. **Caulk 149** may be washed off with **S-10 Cleaning Solvent**, MEK, or lacquer thinner.
- Keep open flames and sparks away from the area where materials are being mixed and applied.



Corporate Offices
1818 Miller Parkway
Streetsboro, OH 44241
330-562-1970
330-562-7638 FAX
www.dudick.com

CAULK 149

**100% SOLIDS, TWO-COMPONENT
POLYSULFIDE EXPANSION/
CONTROL JOINT SEALANT**

- If a rash occurs, remove the individual from the work area and seek a physician's care for dermatitis.
- In case of eye contact, flush with water for at least 15 minutes and consult a physician.
- If swallowed, do not induce vomiting; call a physician immediately.

NOTE: Dudick, Inc. ("Dudick") warrants all goods of its manufacture to be as represented in its catalogs and that the manufacture of its products by its employees or sub-contractors shall be performed in a workmanlike manner. Dudick's sole obligation under this warranty shall be to replace any material which its examination shall disclose to be defective. Dudick makes no warranty concerning the suitability of its product for application to any surface, it being understood that the goods have been selected and the application ordered by the Purchaser. DUDICK, INC. MAKES NO WARRANTY, EXPRESS OR IMPLIED, THAT THE GOODS SHALL BE MERCHANTABLE OR THAT THE GOODS ARE FIT FOR ANY PARTICULAR PURPOSE. THE WARRANTY OF REPAIR OR REPLACEMENT SET FORTH HEREIN IS EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES ARISING BY LAW OR OTHERWISE; AND DUDICK INC. SHALL NOT BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES, INCLUDING BUT NOT LIMITED TO LOST PROFITS, DOWN TIME, DAMAGES TO PROPERTY OF THE PURCHASER OR OTHER PERSONS, OR DAMAGES FOR WHICH THE PURCHASER MAY BE LIABLE TO OTHER PERSONS, WHETHER OR NOT OCCASIONED BY DUDICK'S NEGLIGENCE. This warranty shall not be extended, altered or varied except by written instrument signed by Dudick and Purchaser.

5/23/18