



Corporate Offices  
 1818 Miller Parkway  
 Streetsboro, OH 44241  
 330-562-1970  
 330-562-7638 FAX  
 www.dudick.com

**PROTECTO-GLASS 160XT**

**100% SOLIDS, TROWEL APPLIED,  
 REINFORCED, NOVOLAC EPOXY  
 LINING, 90 MILS (2.3 mm)**

**FEATURES**

State of Florida:  
 Secondary Containment Approval EQ-510  
 Meets all VOC Requirements  
 Low Odor  
 Reinforced to Bridge Small Surface Cracks  
 Can be seeded for anti-skid

**RECOMMENDED APPLICATIONS**

Secondary Containment  
 Concrete Dike Areas  
 Trenches  
 Waste Sumps  
 Acid Storage Areas

**CHEMICAL RESISTANCE**

Sulfuric Acid (98%)                      Alkali Solutions  
 Dilute Inorganic Acids                  Oils  
 Salts  
 Solvents

**TEMPERATURE LIMITS (STEEL)**

Immersion up to 160°F  
 Dry - 200°F - Continuous  
       250°F - Intermittent

**PHYSICAL PROPERTIES**

Compressive Strength ASTM C-579	6,000-7,000 PSI
Tensile Strength ASTM C-307	4,000-5,000 PSI
Flame Spread ASTM D-635	33 mm
Taber Abrasion ASTM D-4060	72 mg.
Tensile Bond Strength ASTM D-7234	Cohesive Failure of Concrete

**SPECIFICATIONS**

**Protecto-Glass 160XT** shall be an amine cured novolac epoxy lining consisting of a 1/16” trowel applied basecoat, one layer of one ounce fiberglass mat reinforcement, and a flake-filled epoxy topcoat as manufactured by Dudick, Inc. Installation shall be in accordance with the manufacturer’s recommended practices.

**THE PROTECTO-GLASS 160 XT SYSTEM**

**Protecto-Glass 160XT** uses a moisture tolerant primer, 1-ounce fiberglass mat reinforcement and a flake-filled novolac topcoat to protect concrete and steel.

**Primer 67:** The primer used in the **Protecto-Glass 160XT System** is a flexibilized epoxy which deeply penetrates the concrete substrate and provides the “wet out” required for good bonding. The primer is tolerant of the residual moisture within the concrete.

**Primer 67C:** is designed for applications on concrete where spark testing is required or specified.

**Basecoat: Protecto-Glass 160XT** uses novolac epoxy resin and silica fillers to reduce the coefficient of expansion and provide a thixotropic base on which to embed the reinforcement.

**Reinforcement:** One ounce chopped strand fiberglass mat is used to help bridge small surface cracks and provide additional strength in tension. It is applied to the wet basecoat and becomes an integral part of it, acting much the same as a reinforcing bar does in concrete.

**Saturant:** Novolac epoxy resin is used to wet out and embed the fiberglass reinforcement, thus providing a mechanical and chemical bond to the basecoat.

**Topcoat:** The novolac epoxy binder and overlapping flake fillers in the **Protecto-Glass 160XT** topcoat provide the low permeability, high film integrity, and chemical resistance required for prolonged substrate protection.

**Optional Broadcast:** Sand or aluminum oxide is used for strength and surface texture; aluminum oxide provides

additional chemical and abrasion resistance. Either material is broadcast to complete saturation and the excess removed by sweeping. Broadcast the aggregate into the topcoat and seal the broadcast with a second topcoat.

**ESTIMATING QUANTITIES AND ORDER BILL OF MATERIAL**

APPROXIMATE SQUARE FEET PER GALLON		
	CONCRETE	STEEL
PRIMER 67	150-200 ft. <sup>2</sup>	275-300 ft. <sup>2</sup>
PRIMER 67C	100-150 ft. <sup>2</sup>	-----
<b>Protecto-Glass 160 XT</b>		
Basecoat & Saturant	25 ft. <sup>2</sup>	
G-1 Filler	.5 lb./ ft. <sup>2</sup>	
Topcoat (15-20 mils)	60-70 ft. <sup>2</sup>	
S-10 Solvent	500 ft. <sup>2</sup>	
<b>Broadcast Options</b>		
Aluminum Oxide	1 - 1¼ lbs./sq.ft.	
Sand	¾ lb./ ft. <sup>2</sup>	

\*Quantities shown are for estimating purposes only. Actual field usage may vary.

\*\*A second topcoat application will be required if system is broadcast with an aggregate.

**APPLICATION INSTRUCTIONS**

**SURFACE PREPARATION**

**Metal:** Abrasive blast to a white metal finish according to SSPC SP5 or NACE # 1 and a 3.0 mil minimum profile.

**Concrete:** Concrete must be prepared mechanically to remove surface laitance and other contaminants. Oils, grease or other contaminant must be removed prior to surface preparation. Concrete must be free of curing compounds and form release agents. Surface texture should be similar to 40-60-grit sandpaper or the visual standard, CSP-5 from the International Concrete Repair Institute **with exposed pea gravel**. The prepared surface should have a minimum tensile strength of 250 PSI per ASTM D-7243.

All concrete substrates must be checked for moisture prior to product application using the Plastic Sheet Test, ASTM D-4263.

Additional surface preparation will be required if a 40-60 grit texture **with exposed pea gravel** is not achieved and the surface laitance not completely removed with the first mechanical preparation procedure.

Mechanical preparation removes laitance, exposing honeycombs or voids beneath the surface which must be filled with **Scratch Coat 300**. (Refer to separate product bulletin.)

**APPLICATION SPECIFICATIONS**

Substrate temperature for both concrete and metal must be between 50°F and 110°F.

Relative humidity must not exceed 90%.

Substrate temperature must be 5°F above the Dew Point.

**PRIMER 67/67C MIX RATIOS**

Primer 67    Component A            1 gallon  
 Primer 67    Component B            1 gallon

Primer 67C   Component A            1 gallon  
 Primer 67C   Component B            29 fl. oz.

**Important: Primer 67C Component A** must be mechanically mixed for 1-2 minutes prior to adding the correct amount of **Component B**.

**Primer 67C** must be roller applied. Use brush application for small touch-up or repair work only.

**PRIMER 67/67 C POT LIFE**

TEMPERATURE	PRIMER 67	PRIMER 67C
50°F	90 min.	110 min.
75°F	60 min.	90 min.
90°F	30 min.	50 min.

**PRIMING**

The following Primers are compatible with **Protecto-Glass 160XT** Primer 67, Primer 67LV, Primer 67DPLV, Primer 67DTO & Primer 60.

Pot life of the mixed **Protecto-Glass 160XT** will depend on the temperature. To prevent material waste, do not mix more than can be used according to the corresponding tables.

**BASECOAT**

TEMPERATURE	POT LIFE
50°F	60 min.
75°F	45 min.
90°F	30 min.



Corporate Offices  
 1818 Miller Parkway  
 Streetsboro, OH 44241  
 330-562-1970  
 330-562-7638 FAX  
 www.dudick.com

**PROTECTO-GLASS 160XT**

**100% SOLIDS, TROWEL APPLIED,  
 REINFORCED, NOVOLAC EPOXY  
 LINING, 90 MILS (2.3 mm)**

Do not attempt to store mixed material. Residual material should be properly disposed of at the end of each work period.

**PROTECTO-GLASS 160XT MIX RATIOS (BY VOLUME)**

**Basecoat and Saturant**

Component A 128 fl.oz.  
 Component B 58 fl. oz.

**Topcoat**

Component A 128 fl.oz.  
 Component B 52 fl. oz.

**BASECOAT**

Add the correct amount of **Component B** to **Component A** and mix thoroughly for 1-2 minutes. Add 18-25 lbs. of **G- 1 Filler** to achieve a mortar-like consistency. Mix well and apply a 1/16” thick basecoat to a smooth, even finish using a plasterer’s trowel.

**REINFORCEMENT AND SATURANT**

Before the basecoat begins to cure, press one layer of 1-ounce fiberglass mat into the wet basecoat. Lap all edges by 1 inch. Use a stiff, natural bristle brush or roller and press the mat firmly into the basecoat, using a technique similar to hanging wallpaper, to remove all air pockets and wrinkles. Saturate the fiberglass with the basecoat resin mixture, using a short nap paint roller. Roll vigorously until the mat has lost its white color and turns translucent. Use enough resin to “wet out” the mat, but do not allow the saturant to puddle. Immediately roll the wet fiberglass with a ribbed roller to remove any trapped air or wrinkles.

Allow the basecoat and reinforcement application to cure overnight. Before applying the topcoat, examine the fiberglass for any air bubbles or blisters. If these are present, they must be cut out and repaired, using the procedure above. All overlapped seams should be sanded flat. The topcoat will emphasize any imperfections in the fiberglass. If excessive blistering of the

basecoat/reinforcement has occurred, it may have been caused by inadequate rolling with the ribbed roller.

**Topcoat**

TEMPERATURE	POT LIFE
50°F	50 min.
75°F	30 min.
90°F	15 min.

**TOPCOAT**

Add the correct amount of **Component B** to **Component A** and mix thoroughly until a uniform color is achieved. Apply at 15-20 mils WFT using a brush, roller or spray to a smooth even finish. Brush or roller application may require additional coats to meet the specified dry film thickness.

**OPTIONAL BROADCAST**

Broadcast 20-40 mesh sand or aluminum oxide into the wet topcoat to complete saturation. Once cured, remove excess with a broom.

To seal in aggregate, apply a second coat of **Protecto-Glass 160XT Topcoat**.

Mix the **Protecto-Glass 160XT Topcoat Component A** for 1-2 minutes to redisperse pigments and fillers. Add the correct amount of **Component B** to **Component A** and mix thoroughly until a uniform color is achieved. Apply at 15-20 mils WFT.

To reduce surface texture, an additional coat should be applied after the topcoat has cured.

Consult Dudick representative for recommendation for spray application.

## Cure Cycles for Protecto-Glass 160XT

TEMPERATURE	RECOAT TIME		CURE TIME
	MIN.	MAX.	
50°F	12-16hrs.	120 hrs.	96 hrs.
75°F	6-8 hrs.	72 hrs.	36 hrs.
90°F	4-6 hrs.	48 hrs.	24 hrs.

If these recoat times are exceeded, consult a Dudick representative. Sanding or abrasive blasting may be required before the next coat. Recoat times are dramatically reduced when the coating is exposed to direct sunlight.

Application of **Protecto-Glass 160XT** in direct sunlight may lead to blistering, pinholes, or wrinkling due to out-gassing of air in the concrete and high substrate temperatures.

Double priming, shading, or evening application may be required. Consult a Dudick representative.

### TESTING

Where immersion service is required, spark testing is mandatory. Use a DC spark/holiday tester set to the appropriate voltage to achieve a minimum 100 volts per mil of applied coating. An AC tester can be used, but is not as effective as a DC tester. Mark and repair all pinholes, using **Protecto-Glass 160XT** topcoat. Retest only the repairs.

### CLEANING

Use **S-10 Cleaning Solvent** to clean tools and equipment.

### SHIPPING

Refer to Material Safety Data Sheets

### STORAGE

**Warning:** All Dudick products classified by DOT with either white, yellow or red labels must not be mixed or stored together as an explosive reaction may occur.

Store all products in a cool, dry area away from open flames, sparks or other hazards.

When stored in their original, unopened containers at 50°F-75°F, **Primer 67** and **Protecto-Glass 160XT** components have a six-month shelf life. **Primer 67C** components will have a thirty-day shelf life. Storage in direct sunlight or excessive heat will reduce working time and shelf life.

## SAFETY

**M.S.D.S:** Material Safety Data Sheets must always be read before using products. **Protecto-Glass 160XT** systems are intended for application by experienced, professional personnel. Dudick, Inc. can supply supervision to help determine that the surface has been properly prepared, the ingredients correctly mixed and the materials properly and safely applied.

If **Protecto-Glass 160XT** materials are to be applied by your own personnel or by a third party contractor, please be sure that they are aware of the following safety precautions:

- Exposure to resins and hardeners through direct skin contact and/or inhalation may cause severe dermatitis reactions in some people. Cleanliness of the skin and clothing is critical and must be of paramount concern.
- Fumes are flammable and heavier than air. Proper ventilation should be maintained to minimize breathing of concentrated fumes.
- Suitable respirators should be used during application.
- Safety glasses, gloves, and suitable protective clothing must be worn at all times during application.
- If contact with hardeners occurs, remove any clothing involved and flush the skin with flowing water. Discard the clothing. Do not attempt to wash and reuse it. **Protecto-Glass 160XT** liquid can be removed with **S-10 Cleaning Solvent**, MEK, or lacquer thinner.
- Keep open flames and sparks away from the area where materials are being mixed and applied.
- If a rash occurs, remove the individual from the work area and seek a physician's care for dermatitis.
- In case of eye contact, flush with water for at least 15 minutes and consult a physician.
- If swallowed, do not induce vomiting; call a physician immediately.

**NOTE:** Dudick, Inc. ("Dudick") warrants all goods of its manufacture to be as represented in its catalogs and that the manufacture of its products by its employees or sub-contractors shall be performed in a workmanlike manner. Dudick's sole obligation under this warranty shall be to replace any material which its examination shall disclose



Corporate Offices  
1818 Miller Parkway  
Streetsboro, OH 44241  
330-562-1970  
330-562-7638 FAX  
www.dudick.com

**PROTECTO-GLASS 160XT**

**100% SOLIDS, TROWEL APPLIED,  
REINFORCED, NOVOLAC EPOXY  
LINING, 90 MILS (2.3 mm)**

to be defective. Dudick makes no warranty concerning the suitability of its product for application to any surface, it being understood that the goods have been selected and the application ordered by the Purchaser. DUDICK, INC. MAKES NO WARRANTY, EXPRESS OR IMPLIED, THAT THE GOODS SHALL BE MERCHANTABLE OR THAT THE GOODS ARE FIT FOR ANY PARTICULAR PURPOSE. THE WARRANTY OF REPAIR OR REPLACEMENT SET FORTH HEREIN IS EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES ARISING BY LAW OR OTHERWISE; AND DUDICK INC. SHALL NOT BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES, INCLUDING BUT NOT LIMITED TO LOST PROFITS, DOWN TIME, DAMAGES TO PROPERTY OF THE PURCHASER OR OTHER PERSONS, OR DAMAGES FOR WHICH THE PURCHASER MAY BE LIABLE TO OTHER PERSONS, WHETHER OR NOT OCCASIONED BY DUDICK'S NEGLIGENCE. This warranty shall not be extended, altered or varied except by written instrument signed by Dudick and Purchaser.

11/11/20