



Dudick inc.

Corporate Offices
1818 Miller Parkway
Streetsboro, OH 44241
330-562-1970
330-562-7638 FAX
www.dudick.com

PROTECTO-LINE 800/805/800AR

**TROWEL APPLIED, REINFORCED,
VINYL ESTER LINING AND FLOOR
TOPPING. 1/8" (3.17 mm)**

FEATURES

FDA Acceptable
Low Permeability
Conductive Version Available

RECOMMENDED APPLICATIONS

Plating Room Floors
Food Processing
Concentrated Acid Spills
Acid Neutralization
Caustic Handling Areas

CHEMICAL RESISTANCE

Inorganic Acids	Organic Acids
Alkali Solutions	Oils
Fluorides (805/800AR)	Salts

**TEMPERATURE LIMITS
(METAL APPLICATION)**

Immersion up to 180° F
Dry - 200°F Continuous
- 250°F Intermittent

PHYSICAL PROPERTIES

Compressive Strength ASTM C-579	12,500 PSI
Coefficient of Expansion ASTM C-531	12-15 x 10 ⁻⁶ in./in./°F
Tensile Strength ASTM C-307	2,400 PSI
ASTM D638	3,400 PSI
Tensile Bond Strength ASTM D-7234	Cohesive failure of concrete
Flexural Strength ASTM C-580	8,600 PSI
Shore D Hardness ASTM D-2240	85-90

Taber Abrasion, CS-17 wheel, 1000 cycles, 1000 gram load ASTM D-4060	40 mg. (G-1) 20 mg. (AR)
Flame Spread ASTM D-635	<5 mm
WVT ASTM E-96	0.0017 perm. in.

Protecto-Line 805
Electrical Properties
ASTM F-150
NFPA #99
0-200,000 Ohms

SPECIFICATIONS

Protecto-Line 800 shall be a nominal 1/8" thick, silica filled vinyl ester lining, consisting of a penetrating primer, 1/16" basecoat, woven fiberglass roving and 1/16" topcoat as manufactured by Dudick, Inc. Materials shall be trowel applied in accordance with manuals recommended practices.

Protecto-line 805 is a vinyl ester based system identical to **Protecto-Line 800**, but utilizes a carbon filler and synthetic fabric in place of the silica filler and glass roving for resistance to fluorides. The carbon filler also provides conductivity.

Protecto-Line 800AR shall be a nominal 1/8" thick vinyl ester lining consisting of a penetrating primer, 1/16" silica filled basecoat, woven fiberglass roving and a 1/ 16" aluminum oxide filled topcoat. Inert aluminum oxide fillers are used to significantly increase resistance to abrasion, fluorides, and strong caustics. A synthetic fabric can be substituted for the glass woven roving for strong fluoride and caustic solutions.



Corporate Offices
 1818 Miller Parkway
 Streetsboro, OH 44241
 330-562-1970
 330-562-7638 FAX
 www.dudick.com

PROTECTO-LINE 800/805/800AR

**TROWEL APPLIED, REINFORCED,
 VINYL ESTER LINING AND FLOOR
 TOPPING. 1/8" (3.17 mm)**

THE PROTECTO-LINE 800/805/800AR SYSTEM

Protecto-Line 800/805/800AR uses several layers of thermosetting, filled vinyl ester resin to build up the protection that metal and concrete need in chemical manufacturing or processing operations. When fully cured, the separate elements lose their individual identity and become a single, monolithic lining.

Primer 27 is designed to prevent abrasive blasted metal from developing rust bloom prior to the application of the **Protecto-Line 800/805/800AR**. For maximum performance, all metal surfaces should be primed. Concrete must be primed to aid in the "wetting out" required for good bonding.

Primer 27C is designed for applications on concrete where spark testing is required or specified.

Basecoat: Protecto-Line 800/805/800AR vinyl ester resins are filled with graded silica or carbon depending on the chemical environment involved to reduce the coefficient of expansion and provide a thixotropic base on which to embed the fiberglass roving or synthetic fabric.

Reinforcement: A woven fiberglass roving or synthetic fabric is used to help bridge small surface cracks and provides additional strength to resist thermal shock. It is applied to the wet basecoat and becomes an integral part of it, acting much the same as a reinforcing bar does in concrete.

Saturant: Catalyzed **Protecto-Line 800/805/ 800AR** vinyl ester resin is used to wet out the reinforcement, thus providing a mechanical and chemical bond.

Topcoat: Protecto-Line 800 systems are aluminum oxide, carbon or silica filled to provide an abrasion and chemical resistant barrier.

**ESTIMATING QUANTITIES AND
 ORDER BILL OF MATERIAL**

Note: Resin includes 3 ozs. hardener/gal. as standard and 6 ozs. for carbon filled.

APPROXIMATE SQUARE FEET PER GALLON		
	CONCRETE	STEEL
PRIMER 27	150-200 ft. ²	250-300 ft. ²
PRIMER 27C	100-150 ft. ²	-----
	P-Line 800	P-Line 805
Basecoat Saturant & Topcoat	16 ft. ²	18 ft. ²
Roving/Fabric	Area + 10%	Area + 10%
G-1 Filler (Silica)	1 lb./ ft. ²	-----
G-9 Filler	-----	0.7 lb. / ft. ² .
S-30 Liquid	150 ft. ²	150 ft. ²
S-10 Solvent	500 ft. ²	500 ft. ²

For **Protecto-Line 800AR** use **AR Filler** at .65 lbs. / ft.² for topcoat.

*Quantities shown are for estimating purposes only. Actual field usage may vary.

During manufacturing, some air entrapment occurs in the more viscous lining systems. During storage and transportation, settling can occur when entrapped air escapes this mix indicating less than 100% volumetric fill. All products are priced and sold by weight and not necessarily by volume

APPLICATION INSTRUCTIONS

SURFACE PREPARATION

Metal: Abrasive blast to a white metal finish according to SSPC SP5 or NACE # 1 and a 3.0 mil minimum profile.



Corporate Offices
 1818 Miller Parkway
 Streetsboro, OH 44241
 330-562-1970
 330-562-7638 FAX
 www.dudick.com

PROTECTO-LINE 800/805/800AR

**TROWEL APPLIED, REINFORCED,
 VINYL ESTER LINING AND FLOOR
 TOPPING. 1/8" (3.17 mm)**

Concrete: Concrete must be mechanically prepared to remove surface laitance. Oils, grease or other contaminant must be removed prior to surface preparation. Concrete must be free of curing compounds and form release agents. Surface texture should be similar to 40-60-grit sandpaper or the visual standard, CSP-5 from the International Concrete Repair Institute **with exposed pea gravel**. The prepared surface should have a nominal tensile strength of 250 PSI per ASTM D-4541.

All concrete substrates must be checked for moisture prior to product application using the Plastic Sheet Test, ASTM D-4263.

Additional surface preparation will be required if a 40-60 grit texture **with exposed pea gravel** is not achieved and the surface laitance not completely removed with the first mechanical preparation procedure.

Abrasive blasting removes laitance, exposing honeycombs or voids beneath the surface that must be filled with **Scratch Coat 800**. (Refer to separate product bulletin.)

APPLICATION SPECIFICATIONS

Substrate temperature for both concrete and metal must be between 50°F and 110°F.

Relative humidity must not exceed 90%.

Substrate temperature must be 5°F above the Dew Point.

Hardener Amount/Gal. Resin:

Hardener	Substrate Temp.	Primer		PL-800/AR Basecoat Topcoat	PL-805 Basecoat Topcoat
		27	27C		
PH-1	60° - 70°F	3-4 oz.	4-5 oz.	3-4 oz.	6-8 oz.
PH-1	70° - 90°F	2-3 oz.	3-4 oz.	2-3 oz.	4-6 oz.

Pot life of the mixed **Protecto-Line 800** systems will depend on the temperature. To prevent material waste and avoid damage to equipment, do not mix more material than can be used according to the following table:

TEMPERATURE	POT LIFE
50 ° F	60 min.
75 ° F	40 min.
90 ° F	25 min.

Do not attempt to store mixed material. Residual material should be properly disposed of at the end of each work period.

PRIMING

Metal: Mix **Primer 27** with the correct amount of **PH- 1 Hardener** for 2-3 minutes and apply with a roller, brush or spray at 3-4 mils WFT.

Concrete: Concrete must always be primed to aid in the “wetting out” required for good bonding. Mix **Primer 27 or 27C** with the correct amount of **PH-1 Hardener** for 2-3 minutes and apply with a brush, roller or spray. Do not allow the primer to puddle.

Always examine the primed surface before beginning the basecoat application. If any dry areas appear, they must be re-primed to insure proper concrete wet out before the lining is applied.

Important: **Primer 27C** must be mechanically mixed for 1-2 minutes prior to adding the correct amount of **PH- 1 Hardener**.

Primer 27C must be roller applied. Use brush application for small touch-up or repair work only.

Consult Dudick representative for recommendation for spray application.



Corporate Offices
 1818 Miller Parkway
 Streetsboro, OH 44241
 330-562-1970
 330-562-7638 FAX
 www.dudick.com

PROTECTO-LINE 800/805/800AR

**TROWEL APPLIED, REINFORCED,
 VINYL ESTER LINING AND FLOOR
 TOPPING. 1/8" (3.17 mm)**

BASECOAT

Add the correct amount of **PH- 1 Hardener** to the resin. Mix thoroughly for 2-3 minutes. For **Protecto-Line 800/800AR**, add 18-25 lbs. of **G-1 Filler**/gal. For **Protecto-Line 805** add 10-15 lbs. of **G-9 Carbon Filler**/gal. Mix well and apply a 1/16" thick basecoat, using a plasterer's trowel. Apply to an even finish.

REINFORCEMENT AND SATURANT

Press the reinforcement into the wet basecoat. Lap all edges by 1 inch. Saturate the reinforcement with catalyzed **Protecto-Line 800/805/800AR** resin using a short nap paint roller. Roll vigorously until the reinforcement has lost its white color and turns translucent. Use enough resin to "wet out" the reinforcement but do not allow the saturant to drip or puddle. It is highly recommended, for good adhesion, that a clean dry sand be lightly broadcast into the wet saturant.

TOPCOAT

Before applying the topcoat, examine the overall application and grind any sharp glass protrusions and fill any voids with catalyzed saturant resin.

Add the correct amount of **PH- 1 Hardener** to the resin. Mix thoroughly for 2-3 minutes. For **Protecto-Line 800**, add 18-25 lbs. **G-1 Filler**/gal. For **Protecto-Line 805**, add 10-15 lbs. **G-9** carbon filler/gal. For **Protecto-Line 800AR**, add 25-30 lbs. **AR Filler**/gal. Mix well and apply a 1/16" thick topcoat, using a plasterer's trowel. Apply to an even finish.

SMOOTHING

Immediately after the trowel application and before the topcoat has cured, dampen a natural bristle brush (thick bristle 4" wide) or roller with S-30 Smoothing Liquid. Lightly brush or roll the wet topcoat to remove trowel marks and pinholes. Never allow S-30 Smoothing Liquid to puddle on the topcoat.

Protecto-Line 800 Systems Cure Cycle:

TEMPERATURE	RECOAT TIME		CURE TIME
	MIN.	MAX.	
50°F	12 hrs.	120 hrs.	96 hrs.
75°F	4 hrs.	96 hrs.	24 hrs.
90°F	3 hrs.	72 hrs.	20 hrs.

If these recoat times are exceeded, consult a Dudick representative; sanding or abrasive blasting may be required before the next coat. Recoat times are dramatically reduced when the coating is exposed to direct sunlight.

Application of **Protecto-Line 800** systems in direct sunlight may lead to blistering, pinholes, or wrinkling due to outgassing of air in the concrete and high substrate temperatures. Double priming, shading, or evening application may be required. Consult a Dudick representative.

In order to prevent curing problems with styrenated products, air movement and/or ventilation must be maintained not only during application but also after application until the system has totally cured. This will prevent high concentration of styrene inhibiting/retarding the cure of the system.

TESTING

If spark testing is required, use a DC spark/holiday tester set to the appropriate voltage to achieve a minimum 100 volts per mil of applied coating. An AC tester can be used, but is not as effective as a DC tester. Mark and repair all pinholes using the topcoat material. Retest only the repairs. Testing of **Protecto-Line 805** is limited to a visual inspection because the lining is conductive.

Concrete: The lining can be spark tested provided **Primer 27C** was used to prime the concrete.

CLEANING

Use **S-10 Cleaning Solvent** to clean tools and equipment. **DO NOT USE ACETONE.**



Dudick inc.

Corporate Offices
1818 Miller Parkway
Streetsboro, OH 44241
330-562-1970
330-562-7638 FAX
www.dudick.com

PROTECTO-LINE 800/805/800AR

**TROWEL APPLIED, REINFORCED,
VINYL ESTER LINING AND FLOOR
TOPPING. 1/8" (3.17 mm)**

SHIPPING

Refer to Material Safety Data Sheets.

STORAGE

Warning: All Dudick products classified by DOT with white, yellow or red labels must not be mixed or stored together as an explosive reaction may occur.

All products should be stored in a cool, dry area away from open flames, sparks or other hazards.

When properly stored in their original, unopened containers at 50°F-75°F, **Primer 27** and the **Protecto-Line 800/805/800AR** components will have a shelf life of three months or less, at temperatures above 75°F, two months or less. **Primer 27C** will have a thirty-day shelf life. **PH-1 Hardener** has a six-month shelf life at 50°F-75°F.

SAFETY

M.S.D.S: Material Safety Data Sheets must always be read before using products. **Protecto-Line 800** systems are intended for application by experienced, professional personnel. Dudick, Inc. can supply supervision to help determine that the surface has been properly prepared, the ingredients correctly mixed, and the materials properly and safely applied.

If **Protecto-Line 800** materials are to be applied by your own personnel or by a third party contractor, please be sure that they are aware of the following safety precautions:

- Exposure to resins and hardeners through direct skin contact and/or inhalation may cause severe dermatitis reactions in some people. Cleanliness of the skin and clothing is critical and must be of paramount concern.
- Fumes are flammable and heavier than air. Proper ventilation should be maintained to minimize breathing of concentrated fumes.

- Suitable respirators should be used during application.
- Safety glasses, gloves, and suitable protective clothing must be worn at all times during application.
- If contact with hardeners occurs, remove any clothing involved and flush the skin with flowing water. Discard the clothing. Do not attempt to wash and reuse it. **Protecto-Line 800** liquid can be removed with S-10 Cleaning Solvent, MEK, or lacquer thinner. **DO NOT USE ACETONE.**
- Keep open flames and sparks away from the area where materials are being mixed and applied.
- If a rash occurs, remove the individual from the work area and seek a physician's care for dermatitis.
- In case of eye contact, flush with water for at least 15 minutes and consult a physician.
- If swallowed, do not induce vomiting; call a physician immediately.

NOTE: Dudick, Inc. ("Dudick") warrants all goods of its manufacture to be as represented in its catalogs and that the manufacture of its products by its employees or sub-contractors shall be performed in a workmanlike manner. Dudick's sole obligation under this warranty shall be to replace any material which its examination shall disclose to be defective. Dudick makes no warranty concerning the suitability of its product for application to any surface, it being understood that the goods have been selected and the application ordered by the Purchaser. DUDICK, INC. MAKES NO WARRANTY, EXPRESS OR IMPLIED, THAT THE GOODS SHALL BE MERCHANTABLE OR THAT THE GOODS ARE FIT FOR ANY PARTICULAR PURPOSE. THE WARRANTY OF REPAIR OR REPLACEMENT SET FORTH HEREIN IS EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES ARISING BY LAW OR OTHERWISE; AND DUDICK INC. SHALL NOT BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES,



Dudick inc.

Corporate Offices
1818 Miller Parkway
Streetsboro, OH 44241
330-562-1970
330-562-7638 FAX
www.dudick.com

PROTECTO-LINE 800/805/800AR

**TROWEL APPLIED, REINFORCED,
VINYL ESTER LINING AND FLOOR
TOPPING. 1/8" (3.17 mm)**

INCLUDING BUT NOT LIMITED TO LOST PROFITS, DOWN TIME, DAMAGES TO PROPERTY OF THE PURCHASER OR OTHER PERSONS, OR DAMAGES FOR WHICH THE PURCHASER MAY BE LIABLE TO OTHER PERSONS, WHETHER OR NOT OCCASIONED BY DUDICK'S NEGLIGENCE. This warranty shall not be extended, altered or varied except by written instrument signed by Dudick and Purchaser.

11/11/20