



Dudick inc.

Corporate Offices
1818 Miller Parkway
Streetsboro, OH 44241
330-562-1970
330-562-7638 FAX
www.dudick.com

SEALER 30

**HIGH SOLIDS, TWO COMPONENT,
ALIPHATIC, POLYURETHANE
SEALER
4-5 mils**

FEATURES

High Solids (4-5 mils DFT/coat)
Excellent Color Stability
Good Stain Resistance
VOC Compliant

RECOMMENDED APPLICATIONS

Clean Rooms Tarmacs
Warehouse Maintenance Floors
Airplane Hangars

CHEMICAL RESISTANCE

Water Oils
Solvents Gasoline
Sodium Hydroxide - 50% Jet Fuel
Dilute Organic/Inorganic Acids

COLORS: Standard Color Chart available upon request. Available in pigmented gloss or satin and in clear gloss, satin and flat.

PHYSICAL PROPERTIES

Solids by Volume 78%
Drying Time, 6 mils WFT 6 hours
Pencil Hardness 2H
Abrasion, ASTM D-4060
CS-17 wheel 25 mg
Impact
 Direct > 160 inch pounds
 Indirect > 160 inch pounds
Gloss 60° 85-90
VOC 10 grams/liter

SPECIFICATIONS

Sealer 30 shall be a two-component, ASTM Type V, aliphatic polyurethane coating applied over repaired and primed concrete as manufactured by Dudick, Inc. Material can be applied by brush, roller or spray in accordance with the manufacturer's recommended practices.

Sealer 30 offers the outstanding color stability and resistance to UV degradation known industry wide to be inherent of aliphatic urethane chemistry. Toughness, impact resistance, and stain resistance are inherent qualities of Sealer 30. Available in gloss and satin, clear or pigmented.

**ESTIMATING QUANTITIES AND
ORDER BILL OF MATERIAL**

APPROXIMATE SQUARE FEET PER GALLON	
CONCRETE	
PRIMER 67LV	150-200 ft. ²
Sealer 30	
Coverage Rate (WFT)	250-300ft. ² @ 6 mils WFT
Actual Coverage Dry	250-300ft. ² @ 4-5 mils DFT
S-10 Solvent	500 ft. ²

**Quantities shown are for estimating purposes only. Actual field usage may vary.

APPLICATION INSTRUCTION

SURFACE PREPARATION

Concrete: Concrete must be prepared mechanically to remove surface laitance. Oils, grease or other contaminant must be removed prior to surface preparation. Concrete must be free of curing compounds and form release agents. Surface texture should be similar to 80-100 grit sandpaper or the visual standard, CSP-1 from the International Concrete Repair Institute. The prepared surface should have a nominal tensile strength of 200 psi per ASTM D-4541.

All concrete substrates must be checked for moisture prior to product application using the Plastic Sheet Test, ASTM D-4263.

Additional surface preparation will be required if a 80-100-grit texture is not achieved and the surface laitance not completely removed after the first mechanical preparation procedure.

Mechanical preparation removes laitance, exposing honeycombs or voids beneath the surface that must be filled with **Scratch Coat 300**. (Refer to separate product bulletin)

APPLICATION SPECIFICATIONS

Substrate temperature for concrete must be between 50°F and 110°F.

Relative humidity must not exceed 90%.

Substrate temperature must be 5°F above the Dew Point.

Sealer 30 Satin and Matte finish retain their gloss properties when stored for three months or longer. After three months gloss levels of unmixed stored materials begin to increase in gloss.

application of **Sealer 30** in direct sunlight may lead to blistering, pinholes, or wrinkling due to outgassing of air in the concrete and high substrate temperatures. Double priming, shading or evening application may be required. Consult a Dudick representative.

PRIMER 67LV MIX RATIO (BY VOLUME)

Component A	1 gallon
Component B	1 gallon

PRIMER 67LV POT LIFE

TEMPERATURE	POT LIFE
50°F	> 90 min.
75°F	60-70 min.
90°F	30-40 min.

SEALER 30 MIX RATIO (BY VOLUME)

Component A	Pre-measured unit
Component B	Pre-measured unit

DO NOT BREAK DOWN UNITS

SEALER 30 POT LIFE

TEMPERATURE	POT LIFE
50°F	90 min.
75°F	60 min.
90°F	45 min.

PRIMING

PRIMER 67LV

Concrete: Concrete must always be primed to aid in the “wetting out” required for good bonding. Mix **Component A and B** for 2-3 minutes and apply with a brush, roller or spray. Do not allow the primer to puddle. **Primer 67LV should be tack free before Sealer is applied.**

Important - With all epoxies after priming and before each additional coat, examine the surface



Dudick inc.

Corporate Offices
1818 Miller Parkway
Streetsboro, OH 44241
330-562-1970
330-562-7638 FAX
www.dudick.com

SEALER 30

**HIGH SOLIDS, TWO COMPONENT,
ALIPHATIC, POLYURETHANE
SEALER
4-5 mils**

for amine blush (oily film). If present, remove by washing with warm water and detergent.

SEALER 30

Mix **Sealer 30 Component A** separately for approximately 1 minute before adding **Component B**. Add the correct amount of **Component B** to **Component A** and mix thoroughly for 2-3 minutes to achieve a uniform color and consistency. Apply at a rate of 240-260 sq. ft./gal. **Sealer 30** cures tack free in 4-5 hours. It will accept foot traffic in 12 hours, light wheel traffic in 24 hours and forklift traffic and chemical exposure in 48 hours. Allow a minimum of 12 hours before applying additional coats. The maximum re-coat time is 72 hours.

SPRAY APPLICATION

Airless spray is recommended for spray applications. Minimum 3000 psi utilizing 0.009-0.011 spray tip orifice. Do not exceed 6 mils WFT.

CLEANING

Use **S-10 Cleaning Solvent** to clean tools and equipment.

SHIPPING

Refer to Material Safety Data Sheets.

STORAGE

Warning: All Dudick products classified by DOT with either white, yellow or red labels, must not be mixed or stored together as an explosive reaction may occur.

All products should be stored in a cool, dry area away from open flames, sparks and other hazards. **Primer 67LV** and **Sealer 30** gloss in storage are stable for six months when properly stored at 50°F-75°F. **Sealer 30** Satin or Matte retain their gloss properties for three months.

Excessive heat may cause premature gelling, reduce working time and shelf life.

Note: **Sealer 30 Component B** contains aliphatic isocyanates that will react with moisture. Partially used containers should be blanketed with nitrogen and tightly sealed if prolonged storage is anticipated.

SAFETY

M.S.D.S: **Material Safety Data Sheets must always be read before using products.** **Sealer 30** is intended for application by experienced, professional personnel. Dudick, Inc. can supply supervision to help determine that the surface has been properly prepared, the ingredients correctly mixed, and the materials properly and safely applied.

If **Sealer 30** is to be applied by your own personnel or by a third party contractor, please be sure that they are aware of the following safety precautions:

- Exposure to resins and hardeners through direct skin contact and/or inhalation may cause severe dermatitis reactions in some people. Cleanliness of the skin and clothing is critical and must be of paramount concern.
- Fumes are flammable and heavier than air. Proper ventilation should be maintained to minimize breathing of concentrated fumes.
- Suitable respirators should be used during application.
- Safety glasses, gloves, and suitable protective clothing must be worn at all times during application.
- If contact with hardeners occurs, remove any clothing involved and flush the skin with flowing water. Discard the clothing. Do not attempt to wash and reuse it. **Sealer 30** liquid can be removed with S-10 Cleaning Solvent, MEK or lacquer thinner.
- Keep open flames and sparks away from the area where materials are being mixed and applied.
- If a rash occurs, remove the individual from the work area and seek a physician's care for dermatitis.
- In case of eye contact, flush with water for at least 15 minutes and consult a physician.
- If swallowed, do not induce vomiting; call a physician immediately.

NOTE: Dudick, Inc. ("Dudick") warrants all goods of its manufacture to be as represented in its catalogs and that the manufacture of its products by its employees or sub-contractors shall be performed in a workmanlike manner. Dudick's sole obligation under this warranty shall be to replace any material which its examination

shall disclose to be defective. Dudick makes no warranty concerning the suitability of its product for application to any surface, it being understood that the goods have been selected and the application ordered by the Purchaser. DUDICK, INC. MAKES NO WARRANTY, EXPRESS OR IMPLIED, THAT THE GOODS SHALL BE MERCHANTABLE OR THAT THE GOODS ARE FIT FOR ANY PARTICULAR PURPOSE. THE WARRANTY OF REPAIR OR REPLACEMENT SET FORTH HEREIN IS EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES ARISING BY LAW OR OTHERWISE; AND DUDICK INC. SHALL NOT BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES, INCLUDING BUT NOT LIMITED TO LOST PROFITS, DOWN TIME, DAMAGES TO PROPERTY OF THE PURCHASER OR OTHER PERSONS, OR DAMAGES FOR WHICH THE PURCHASER MAY BE LIABLE TO OTHER PERSONS, WHETHER OR NOT OCCASIONED BY DUDICK'S NEGLIGENCE. This warranty shall not be extended, altered or varied except by written instrument signed by Dudick and Purchaser.

03/26/18