

SELECTION & SPECIFICATION DATA

Generic Type	Two-component, water-borne aliphatic urethane wall coating
Description	Steri-Coat 200 offers the abrasion resistance and toughness inherent of urethanes. It also provides excellent resistance to UV discoloration and staining.
Features	<ul style="list-style-type: none"> • Class A Fire Rating • Meets SCAQMD Rule 1113 for VOC content • Low odor • Low VOC's • Excellent adhesion • Excellent chemical & abrasion resistance • Excellent stain resistance • Anti-Microbial Agents are available as an option • Soap & water clean up • Also available in satin
Color	Standard color chart available upon request.
Finish	Gloss
Primer	Dudick Primer 200WB Other epoxy basecoats may be used based on exposure and environment. Contact your representative for recommendations.
Dry Film Thickness	3 - 4 mils (76 - 102 microns) per coat Multiple coats may be required depending on color selection and substrate.
Typical Uses	<ul style="list-style-type: none"> • Research Facilities • Laboratories • Food & Beverage Facilities • Hospitals • High Containment Bio-Safety Research Lab (BSL) 1-3
Solids Content	By Volume 50% +/- 2%
Theoretical Coverage Rate	802 ft ² /gal at 1.0 mils (19.7 m ² /l at 25 microns) 267 ft ² /gal at 3.0 mils (6.6 m ² /l at 75 microns) 200 ft ² /gal at 4.0 mils (4.9 m ² /l at 100 microns) Allow for loss in mixing and application.
VOC Values	As Supplied : <50 g/l

SUBSTRATES & SURFACE PREPARATION

Concrete or CMU | Concrete must be prepared mechanically to remove surface laitance exposing honeycombs or voids beneath the surface that must be filled with Scratch-Coat 300. Oils, grease or other contaminant must be removed prior to surface preparation. Concrete must be free of curing compounds and form release agents. Surface texture should be similar to 80-100 grit sandpaper or the visual standard, CSP-1 from the International concrete Repair Institute. The prepared surface should have a minimum tensile strength of 200 PSI per ASTM D-4541. All concrete substrates must be checked for moisture prior to product application using the Plastic Sheet Test, ASTM D-4263. Additional surface preparation will be required if a 80-100 grit texture is not achieved and the surface laitance not completely removed with the first mechanical preparation procedure.

CMU:CMU surfaces are to be lightly abrasive blasted to clean CMU block and to provide a 60-80 grit sandpaper texture of the mortar joints. Care must be taken not to damage CMU.

Drywall & Plaster | Consult your representative for preparation methods.

PERFORMANCE DATA (TYPICAL VALUES)

Test Method	Results
Adhesion, ASTM D-3359	5B over cured epoxy
Chemical Resistance, ASTM D-1308, 24 hour spot test	No effect water, 2% Sulfuric Acid, 6% H2O2, Idophores 2000ppm, Toluene, Xylene, 10% NaOH, 70% ethanol
Flame Rating	Class A
Flame Spread Index	5
QUV Resistance, Accelerated Weathering ASTM D-4324/G53	Gloss 95%+ retention after 1000 hours delta E color change – 0.15 after 1000 hours. No blistering, rusting, checking or cracking
Shore D Hardness, ASTM D-2240	80
Smoke Dev Index	5
Tear Strength ASTM D-624 Die C	450 psi (3.1 MPa)
Tensile Strength ASTM D-638	8500 psi (58.6 MPa)

Consult your representative for further information on chemical resistance.

MIXING & THINNING

Mixing | Mechanically mix the Steri-Coat 200 Component A separately for 1-2 minutes to disperse any pigments or fillers which have settled. Add Component B and mix until a uniform color is achieved. Steri-Coat 200 is provided in pre-measured units. **Do not break units down. DO NOT MIX PARTIAL KITS.**

Thinning | **DO NOT THIN**

Ratio | 5:1 by volume

APPLICATION EQUIPMENT GUIDELINES

Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results.

Spray Application | Contact Dudick representative for recommendations for spray applications.

APPLICATION EQUIPMENT GUIDELINES

Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results.

Brush & Roller (General)	Use a short-nap mohair roller cover with solvent resistant core. For best results, condition roller before application to minimize lint or loose fibers. A high quality solvent resistant brush may be used for hard to reach areas. Use Brush application for touch-up or cutting in only.
---	---

APPLICATION CONDITIONS

Condition	Surface	Humidity
Minimum	50°F (10°C)	0%
Maximum	90°F (32°C)	90%

Substrate temperature must be 5°F (3°C) above the Dew Point.
 Do not apply Steri-Coat 200 in direct sunlight.

CURING SCHEDULE

Surface Temp.	Dry to Touch	Dry Hard	Final Cure	Maximum Recoat
70°F (21°C)	6 Hours	24 Hours	14 Days	14 Days

Values above are based on 50% relative humidity.
 Contact Dudick representative if max recoat window is exceeded.

TESTING / CERTIFICATION / LISTING

General	Dudick flooring systems can be built to meet or exceed the requirements of Static or Dynamic Coefficient of Friction testing per installation to meet static coefficient of friction requirements for ANSI B101.1 of >0.6 and dynamic coefficient of friction (DCOF)* – Wet ANSI A326.3 of >0.42.
----------------	---

CLEANUP & SAFETY

Cleanup	Clean all tools and spray equipment immediately after use with warm water. Acetone may be used as a final rinse.
Safety	Read and follow all caution statements on this product data sheet and on the SDS. Employ normal safety precautions. Keep container closed when not in use.

PACKAGING, HANDLING & STORAGE

Shelf Life	6 months @ 50°F-75°F (10°C-24°C) Exposure to excessive heat may cause premature gelling, reduce working time and shelf life.
Storage Temperature & Humidity	Protect from freezing! If frozen, contact Dudick representative.

Steri-Coat 200

PRODUCT DATA SHEET



WARRANTY

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Carboline Company to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Carboline quality control. We assume no responsibility for coverage, performance, injuries or damages resulting from use. Carbolines sole obligation, if any, is to replace or refund the purchase price of the Carboline product(s) proven to be defective, at Carbolines option. Carboline shall not be liable for any loss or damage. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. All of the trademarks referenced above are the property of Carboline International Corporation unless otherwise indicated.