



DUDICK, INC.

Corporate Offices
1818 Miller Parkway
Streetsboro, OH 44241
330-562-1970
800-322-1970
330-562-7638 FAX
www.dudick.com

STERI-FLOR GP SEMI SELF-LEVELING OR SEEDED HIGH SOLIDS GENERAL PURPOSE EPOXY TOPPING 10-15 mils (.25-.38 mm)

GREEN BUILDING FEATURES

Contributes toward satisfying credit for low emitting material under LEED 4.1

Meets California Department of Public Health CDPH/EHLB Standard Method Version 1.2 2017 Compliance Certificates Available Upon Request

- Low VOC emitting material
- Low VOC's
- Low installation odor
- Contains 15% post industrial recycled product

APPLICATION FEATURES

- High solids general purpose epoxy
- Semi self leveling to a high-gloss finish at 10-12 mils.
- Can be seeded for anti-skid surface.
- Stain resistant with excellent cleanability.
- Can saturate fiberglass reinforcement for better crack bridging properties.
- USDA Compliant

CHEMICAL RESISTANCE

- Dilute Inorganic Acids
- Dilute Alkali Solutions
- Cleaning & Sanitizing Solutions
- Mineral Oils
- Salt Solutions

TYPICAL APPLICATIONS

- Food Processing Floors
- Laboratories
- Pharmaceutical Plants
- Waste Water Treatment Facilities
- Aisleways
- Printed Circuit Board Facilities

COLORS: Available in Standard Floor Colors

- Light Gray
- Medium Gray
- Dark Gray
- Tan
- Tile Red
- Beige
- Light Blue
- Dark Blue
- Light Green
- Dark Green

TYPICAL PROPERTIES

Compressive Strength ASTM C579	12,000 PSI (82.7 MPa)
Compressive Strength ASTM D695	21,000 PSI (144.8 MPa)
Tensile Strength ASTM C307	5,000 PSI (34.5 MPa)
Tensile Strength ASTM D638	7,200 PSI (49.6 MPa)
Flexural Strength ASTM C580	11,500 PSI (79 MPa)
Shore D Hardness ASTM D2240	85-90
Tensile Bond Strength ASTM D7234	Cohesive failure of concrete
Taber Abrasion ASTM D4060	32 mg

SPECIFICATIONS

Steri-Flor GP shall be a 10-15 mils thick, semi-self leveling, high solids multifunctional epoxy floor topping.

Steri-Flor GP is manufactured by Dudick, Inc. and applied in accordance with the manufacturer's recommendations.

THE STERI-FLOR GP SYSTEM

Steri-Flor GP uses a moisture-tolerant primer and a semi-self leveling topcoat to achieve a strongly bonded monolithic topping with moderate chemical resistance and good physical and mechanical properties.

Primer: The blasted concrete surface must be primed to provide the "wetting out" required for good bonding. **Steri-Flor GP** can be applied while the primer is still tacky. Do not allow the primer to puddle.

Topcoat: The semi-self-leveling **Steri-Flor GP** develops a cured strength 2-3 times that of the concrete base to which it is applied to provide exceptional durability and prolong the life of the substrate.

**ESTIMATING QUANTITIES AND ORDER
BILL OF MATERIAL**

THEORETICAL SQUARE FEET PER GALLON AT 10-12 MILS**	
Primer	See specified Primer Data Sheet
Steri-Flor GP Topcoat	120-160 ft ²

**Quantities shown are for estimating purposes only. Actual field usage may vary.

SURFACE PREPARATION

Concrete: Concrete must be prepared mechanically to remove surface laitance. Oils, grease or other contaminant must be removed prior to surface preparation. Concrete must be free of curing compounds and form release agents. Surface texture should be similar to 60-80 grit sandpaper or the visual standard, CSP-3 from the International Concrete Repair Institute. The prepared surface should have a nominal tensile strength of 225 PSI per ASTM D7234.

All concrete substrates must be checked for moisture prior to product application using the Plastic Sheet test, ASTM D4263.

Additional surface preparation will be required if a 60-80 grit texture is not achieved and the surface laitance not completely removed with first mechanical preparation procedure.

Mechanical preparation removes laitance, exposing honeycombs or voids beneath the surface, which can be filled with **Scratch Coat 300**. (Refer to separate product bulletin)

ENVIRONMENTAL CONDITIONS

Temperature of concrete substrate must be between 50°F and 110°F.

Relative humidity must not exceed 90%.

Substrate temperature must be 5°F above the Dew Point.

PRIMING

The following Primers are compatible with **Steri-Flor GP**: Primer 67, Primer 67LV, Primer 67DPLV, Primer 67DTO & Primer 60.

BASECOAT / TOPCOAT

STERI-FLOR GP MIX RATIO (BY VOLUME)

Component A 84 oz.
Component B 44 oz.

POT LIFE AND CURE TIME

Temperature	Pot Life	Cure Time
50°F	50-60 min.	72 hrs.
75°F	30-40 min.	24 hrs.
90°F	20-30 min.	20 hrs.

TOPCOAT

Prior to adding **Component B**, mix **Steri-Flor GP Component A** for 1-2 minutes to assure that any pigment or filler, which may have settled, is dispersed so that a uniform color is achieved. Combine the **A and B Components** and stir mechanically for approximately 2-3 minutes to achieve a uniform color and consistency. Pour the **Steri-Flor GP** mix directly onto the primed concrete.

The mix should be spread to a 10-12 mil thickness with a serrated squeegee, notched trowel or gauge rake. The gauge rake is preferred. After spreading the material to the proper thickness, roll with a short nap roller to level.

To terminate work, use duct tape to set a straight edge and remove the tape when the topping becomes lightly tacky. Start the next work period butting into this area. Permanent terminating lines should be made into the saw cuts in the concrete.

OPTIONAL SEALERS

For **improved** UV stability, abrasion, stain resistance and chemical resistance. A Sealer can be applied over **Steri-Flor GP**. Consult Dudick for best options.

NOTES

Important - With all epoxies after priming and before each additional coat, examine the surface for amine blush (oily film). If present, remove by washing with warm water and detergent.

The Pot life of **Steri Flor GP** system components will depend upon the temperature. To prevent material waste and avoid damage to equipment, do not mix more material then can be used according to the corresponding Pot Life & Cure Time charts.

Do not attempt to store mixed material. Residual material should be properly disposed of at the end of each work period.

Application of **Steri-Flor GP** in direct sunlight may lead to blistering, pinholes, or wrinkling due to outgassing of air in the concrete and high substrate temperatures. Double priming, shading or evening application may be required. Consult a Dudick representative.



DUDICK, INC.

Corporate Offices
1818 Miller Parkway
Streetsboro, OH 44241
330-562-1970
800-322-1970
330-562-7638 FAX
www.dudick.com

STERI-FLOR GP SEMI SELF-LEVELING OR SEEDED HIGH SOLIDS GENERAL PURPOSE EPOXY TOPPING 10-15 mils (.25-.38 mm)

Steri-Flor GP system is intended for interior use only.

CLEAN UP

Use **S-10 Cleaning Solvent, MEK or Acetone** to clean tools and equipment. **DO NOT USE LACQUER THINNER.**

SHIPPING

Refer to Material Safety Data Sheets.

STORAGE

Warning: All Dudick products classified by DOT with either white, yellow, or red labels must not be mixed or stored together as an explosive reaction can occur.

Store all products in a cool, dry area away from open flames, sparks, or other hazards.

When stored in their original, unopened containers at 50°F-75°F, **Primers** and **Steri-Flor GP** components will have a six-month shelf life. Storage in direct sunlight or excessive heat will reduce working time and shelf life.

SAFETY

M.S.D.S.: **Material Safety Data Sheets** must always be read before using products. **Steri-Flor GP** materials are intended for application by experienced, professional personnel. Dudick, Inc., can supply supervision to help determine that the surface has been properly prepared, the ingredients correctly mixed, and the materials properly and safely applied.

If **Steri-Flor GP** is to be applied by your own personnel or by a third party contractor, please be sure that they are aware of the following safety precautions:

- Exposure to resins and hardeners through direct skin contact and/or inhalation may cause severe dermatitis reactions in some people. Cleanliness of the skin and clothing is critical and must be of paramount concern.
- Fumes are flammable and heavier than air. Proper ventilation should be maintained to minimize breathing of concentrated fumes.

- Suitable respirators should be used during application.
- Safety glasses, gloves, and suitable protective clothing must be worn at all times during application.
- If contact with hardeners occurs, remove any clothing involved and flush the skin with flowing water. Discard the clothing. Do not attempt to wash and reuse it. **Steri-Flor GP** liquid can be removed with **S-10 Cleaning Solvent, MEK, or Acetone.**
- Keep open flames and sparks away from the area where materials are being mixed and applied.
- If a rash occurs, remove the individual from the work area and seek a physician's care for dermatitis.
- In case of eye contact; flush with water for at least 15 minutes and consult a physician.
- If swallowed, do not induce vomiting; call a physician immediately.

NOTE: Dudick, Inc. ("Dudick") warrants all goods of its manufacture to be as represented in its catalogs and that the manufacture of its products by its employees or sub-contractors shall be performed in a workmanlike manner. Dudick's sole obligation under this warranty shall be to replace any material which its examination shall disclose to be defective. Dudick makes no warranty concerning the suitability of its product for application to any surface, it being understood that the goods have been selected and the application ordered by the Purchaser. DUDICK, INC. MAKES NO WARRANTY, EXPRESS OR IMPLIED, THAT THE GOODS SHALL BE MERCHANTABLE OR THAT THE GOODS ARE FIT FOR ANY PARTICULAR PURPOSE. THE WARRANTY OF REPAIR OR REPLACEMENT SET FORTH HEREIN IS EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES ARISING BY LAW OR OTHERWISE; AND DUDICK INC. SHALL NOT BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES, INCLUDING BUT NOT LIMITED TO LOST PROFITS, DOWN TIME, DAMAGES TO PROPERTY OF THE PURCHASER OR OTHER PERSONS, OR DAMAGES FOR WHICH THE PURCHASER MAY BE LIABLE TO OTHER PERSONS,

WHETHER OR NOT OCCASIONED BY DUDICK'S NEGLIGENCE. This warranty shall not be extended, altered or varied except by written instrument signed by Dudick and Purchaser.

06/30/21